

CoreLite® PVC

Product Data Sheet

Last Revised: December 14, 2015

CoreLite® PVC is a closed-cell, cross-linked polymer PVC foam formulated for durability, strength, and high processing temperatures. It is compatible with multiple resins and adhesives.

It has a very low water absorption rate and excellent chemical resistance. Ideal for many lightweight composite applications.

PROCESSING

- Hand lamination / spray lay-up
- Vacuum infusion
- Resin injection
- Adhesive bonding
- Pre-preg processing (up to 80 °C, 176 °F)
- Thermoforming



APPLICATIONS

Marine: hulls, decking, bulkheads, interiors superstructures

Transportation: floors, ceilings, doors, interiors, partition walls, sidewalls

Wind energy: rotor blades, covers, casings

Aerospace: fuselage and wind components, kitchen trolleys, galleys

Industrial: Covers, Containers, Tanks, Sporting goods, Tooling and Molds

Asia
2/F Leader CTR 37 Wong Chuk
Hang Rd Aberdeen
Hong Kong
T +852 8193 3434

North America
1060 E. 30 St.
Miami, FL 33013
USA
T +1 (305) 921-4292

South America
Km. 24 Via Daule
Guayaquil
Ecuador
T +593 4-226-7008

Europe
Via Enrico Fermi, 170
46011 – Acquanegra s/C (MN)
Italy
T +39 3398 107391

CoreLite® PVC

Mechanical Properties for CoreLite® PVC

TEST STANDARDS		Units (Imperial)	40	48	60	80	100	130	200	250
Density	ASTM D1622	Lbs. / cu.ft	2.5	3	3.75	5	6.24	8.12	12.5	15.7
Compressive Strength	ASTM D1621-10	psi	74	100	139	207	280	396	699	949
Compressive Modulus	ASTM D1621-10	psi	4061	4786	6672	9862	13053	18130	30168	40176
Tensile Strength	ASTM D1623	psi	107	138	306	377	447	553	935	1031
Tensile Modulus	ASTM D1623	psi	10733	12618	15374	19870	24511	31328	58885	62221
Shear Strength	ASTM C273	psi	65	80	112	164	216	294	497	677
Shear Modulus	ASTM C273	psi	1885	2321	3046	4206	5366	7107	11023	13924
Shear elongation at break	ASTM C273	%	5	9	13	20	25	32	41	40
Thermal conductivity at 75 °F	ASTM C-177	BTU.in/ft2.hr.°F	0.21	0.21	0.21	0.23	0.24	0.27	0.33	0.39
Standard Sheet (Plain)	Length	inch	112.20	107.48	96.45	85.83	80.71	74.80	62.99	59.06
	Width	inch	52.36	50.00	45.27	40.16	37.40	33.47	29.53	27.56
	Thickness	inch	1/8 to 3 ¼	1/8 to 2 ¾	1/8 to 2 ¾	1/8 to 2 ¾	1/8 to 2 ½	1/8 to 2	1/8 to 1 ¾	1/8 to 1 ¾

Values shown are nominal average determined from independent laboratory and house testing. Tests are perpendicular to the plane.

Color:	Light Blue	Purple	Yellow	Green	Pink	Blue	Brown	Dark Green
Density Tolerance:	+ / - 10%							
Water absorption	< 1%							
Processing temperature:	176 °F							

Disclaimer: The information and data presented herein are subject to revision. CoreLite reserves the right to release replacement data. The data presented is derived from in house and independent testing. Calculations should be verified with physical test. The data is provided without liability to CoreLite or its agents and does not constitute warranty or representation in respect to the material or its use. To be used for information only.

CoreLite® PVC

Mechanical Properties for CoreLite® PVC

TEST STANDARDS		Units (Metric)	40	48	60	80	100	130	200	250
Density	ASTM D1622	Kg. / m ³	40	48	60	80	100	130	200	250
Compressive Strength	ASTM D1621-10	MPa	0,51	0,69	0,96	1,43	1,93	2,73	4,82	6,54
Compressive Modulus	ASTM D1621-10	MPa	28	33	46	68	90	125	208	277
Tensile Strength	ASTM D1623	MPa	0,74	0,95	2,11	2,60	3,08	3,81	6,45	7,11
Tensile Modulus	ASTM D1623	MPa	74	87	106	137	169	216	406	429
Shear Strength	ASTM C273	MPa	0,45	0,55	0,77	1,13	1,49	2,03	3,43	4,67
Shear Modulus	ASTM C273	MPa	13	16	21	29	37	49	76	96
Shear elongation at break	ASTM C273	%	5	9	13	20	25	32	41	40
Thermal conductivity at 24 °C	ASTM C-177	W/m.K	0,031	0,031	0,031	0,033	0,035	0,039	0,048	0,056
Standard Sheet (Plain)	Length	mm	2850	2730	2450	2180	2050	1900	1600	1500
	Width	mm	1330	1270	1150	1020	950	850	750	700
	Thickness	mm	3 to 80	3 to 70	3 to 70	3 to 70	3 to 64	3 to 51	3 to 45	3 to 45

Values shown are nominal average determined from independent laboratory and house testing. Tests are perpendicular to the plane.

Color:								
Density Tolerance:	+ / - 10%							
Water absorption	< 1%							
Processing temperature:	80 °C							

Disclaimer: The information and data presented herein are subject to revision. CoreLite reserves the right to release replacement data. The data presented is derived from in house and independent testing. Calculations should be verified with physical test. The data is provided without liability to CoreLite or its agents and does not constitute warranty or representation in respect to the material or its use. To be used for information only.

Driven by innovation,
inspired by **possibilities**,
powered by **nature**,
built for **you**,
we are proud to make the most
sustainable core material on earth.

Learn more



imagine.
create.
enjoy.

Asia
2/F Leader CTR 37 Wong Chuk
Hang Rd Aberdeen
Hong Kong
T +852 8193 3434

North America
1060 E. 30 St.
Miami, FL 33013
USA
T +1 (305) 921-4292

South America
Km. 24 Via Daule
Guayaquil
Ecuador
T +593 4-226-7008

Europe
Via Enrico Fermi, 170
46011 – Acquanegra s/C (MN)
Italy
T +39 3398 107391